

TECHNICAL DATA SHEET

UL-2289-3

ISSUE DATE: 08/31/2010

PRODUCT DESCRIPTION	UL-2289-3 is a reactive polyurethane liquid for R.V.	
USES	Specifically designed for the production of R.V. panels. Also used for the production of Engineered Wood components.	
FEATURES	<ul style="list-style-type: none">• Superb adhesion to PS foam, plastics and Luan boards• Moderate open and cure time• Very good temperature, moisture and aging resistance• Passes ASTM D1183 test• Excellent stability	
TECHNICAL PROPERTIES	Viscosity:	6,000 cPs ± 2,000 cPs
	Specific weight:	9.3 lbs/gallon
	Open time:	7 minutes
	Press time:	20 minutes
PRODUCT APPLICATION	Designed for extrusion and closed roll-coater systems	
ADDITIONAL DATA	Application temp: Ambient	Color @ room temp: Tan Liquid
	DURA-PUR [®] UC-2045 for daily cleaning and purging of application and delivery system.	
PACK SIZES	250 gallon totes	55 gallon closed head drums
	5 gallon pails	300 ml plastic caulk tubes
STORAGE CONDITIONS	Store indoors in a clean, dry space.	
LIMITATIONS	Shelf life: 6 - 12 months.	

Any recommendations contained herein or any information given by any IFS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision. It is the user's responsibility to ensure that this sheet is current prior to using the product.